



DUROXITE 100 WIRE

DUROXITE 100 WIRE

General Product Description

Duroxite 100 WIRE is a flux-cored welding wire for hardfacing components subject to severe sliding wear and moderate to low impact applications using an open-arc welding process. The weld deposit contains abrasion-resistant materials composed of a high proportion of extremely hard primary M_7C_3 chromium-rich carbides. With a typical hardness of 1700 HK¹⁾ these carbides are dispersed evenly in a ductile eutectic austenite matrix. It naturally reveals stress-relief cracks after welding. Duroxite 100 WIRE is suitable for single-layer or multiple-layer deposits up to a maximum of three layers.

¹⁾ HK is the Knoop microhardness used primarily for very brittle materials.

Key Benefits

- Same wear resistance guaranteed from surface through 75% depth of overlay in multi-layer deposit
- Optimal alloy formulation that forms a carbide composition which provides a good combination of wear resistance and homogenous bonding

Typical Applications

Duroxite 100 WIRE is mainly designed to use for hardfacing wear parts undergoing wear by earth, sand and abrasives up to 350°C (660°F). Typical examples include: Crusher hammers, gyratory crusher cones and mantles, dredging pumps, slurry pipes, dragline bucket liners, coal pulverizer rolls, coke hammers, sand dredging parts, mining and earthmoving components, and sorting screens.

Standard Dimensions

Standard Diameter	Metric	Imperial
	1.6 mm	1/16"

Wear Properties

Number of overlay passes	ASTM G65 – Procedure A weight loss ³⁾	
	Surface	75% depth of overlay ⁴⁾
Multiple passes	0.18 g maximum	0.18 g maximum

³⁾ ASTM G65 is a standard test measuring sliding abrasion resistance using a dry sand/rubber wheel apparatus. ASTM G65-Procedure A is the most severe test method.

⁴⁾ ASTM G65 wear test is conducted at 75% depth of the overlay materials to ensure consistently good wear resistance from the top surface through to the depth of 75% of the overlay.

DUROXITE 100 WIRE

Mechanical Properties

Classifications

DIN 14700 T Fe15 g

DIN 8555 MF 10 GF 60 G

Typical all-weld metal chemical composition (wt. %)

C	Mn	Si	Cr	Fe
4.7	0.2	0.6	27.0	Balance

Typical all-weld metal surface hardness ²⁾

Three-layer deposit on mild steel: 60–62 HRC

²⁾ Surface hardness is measured on machined flat surface just below overlay surface.

Welding recommendations

Welding conditions

Current type	Shielding gas	Welding positions
DCEP (Direct current electrode positive)	None (Self-shielded)	Flat, half up, half down

Welding parameters

Diameter		Amperage (A)		Voltage (V)		Stick-out			
						Range		Optimum	
Metric	Imperial	Range	Optimum	Range	Optimum	Metric	Imperial	Metric	Imperial
1.6 mm	1/16"	150–270	200	24–27	25	20 mm–40 mm	3/4"–1-5/8"	25 mm	1"

Recovery: 90%

Delivery Conditions

Standard package	Diameter		Type	Weight	
	Metric	Imperial		Metric	Imperial
	1.6 mm	1/16"	Spool	15 kg	33 lb

Fabrication and Other Recommendations

The welded overlay components can be processed by welding, cutting, forming and machining. Specific recommendations can be found in the Duroxite Product brochure or by consulting your local technical support representative.

The English version of this document shall prevail in case of discrepancy. Download the latest version of this document at www.ssab.com.

SSAB, Strenx™, Hardox®, Docol®, GreenCoat®, Toolox®, Armox®, Domex®, Raex®, and Duroxite™ are trademarks owned by the SSAB group of companies..